

BELZONA REBUILDS ERODED RUDDER PINTLE HOUSING

CUSTOMER

BC, Canada

APPLICATION DATE

August 1999

APPLICATION SITUATION

Eroded rudder pintle housing

PROBLEM

Bi-metallic corrosion had eroded much of the metal (about 1/4 inch) from the rudder pintle housing.

PRODUCTS

Belzona 1311 (Ceramic R-Metal)

Belzona 1321 (Ceramic S-Metal)

SUBSTRATE

Mild steel

APPLICATION METHOD

The application was carried out in accordance with Belzona Know-How System Leaflet SOS-3.

BELZONA FACTS

Using Belzona eliminated the need for extensive welding and line boring. The application was completed in less than 12 hours.

PICTURES

1. View of blasted rudder housing.
2. Housing coated with Belzona 1321 to increase slip factor.
3. Rudder in position on horizontal slide partially inserted.
4. Rudder pintle inserted and allowed to set up before being removed with the aid of a 30 ton hydraulic jack. The reformed bore was inspected by the ships insurers and found to provide almost 100% contact.



For more examples of *Belzona Know-How In Action*, please visit <http://khia.belzona.com>



ISO 9001:2008
Q 09335
ISO 14001:2004
EMS 509612

Belzona products are
manufactured under an ISO
9000 Registered Quality
Management System.

UK • USA • Canada • Thailand
www.belzona.com


BELZONA
Repair • Protect • Improve