

BELZONA PROVEN CAVITATION PROTECTION TO FRANCIS TURBINE

ID: 1441

Industry: Power
Application: CEP-Centrifugal Pumps
Substrate: Cast Iron
Products: * Belzona® 1311 (Ceramic R Metal) Belzona® 1341 (Supermetalgilde) Belzona® 2141 (ACR Elastomer),

Customer Location: Hydroelectric plant, Slovakia
Application Date: 2004 and 2007

Problem

Cavitation had caused erosion of the metal and loss of turbine performance. Belzona® 1311 and Belzona® 1341 had been applied in 2004, but had suffered further cavitation, so system upgraded by applying more cavitation resistant Belzona® 2141.



Photograph Descriptions

- * Cavitation damage to turbine runner ,
- * Belzona® 1341 showing some cavitation damage ,
- * Belzona® 2141 being applied to the runner ,
- * After 24 months service Belzona® 2141, inspection shows no further cavitation damage ,

Application Situation

Francis turbine runner, 800mm diameter, 40-50m head and optimum 600rpm. Power output 2.1MW with 4m³/s flow rate.

Application Method

Application was carried out in accordance with Belzona Know-How System Leaflets CEP-3 and CEP-10

For more examples of Belzona Know - How In Action, please visit <https://khia.belzona.com>

ISO 9001:2015
 FS 695214
 ISO 14001:2015
 EMS 695213

Belzona products are
 manufactured under an ISO
 9000 Registered Quality
 Management System.

www.belzona.com


BELZONA
 Repair • Protect • Improve

Belzona Facts

Inspection of the Belzona Ceramic coating in 2006 showed damage from cavitation, so specification was changed to Belzona® 2141. Further inspection after 2 years showed no damage on the turbine runner.

In 2013 small areas of coating damage were repaired with further Belzona 2141.

For more examples of Belzona Know - How In Action, please visit <https://khia.belzona.com>

ISO 9001:2015
FS 695214
ISO 14001:2015
EMS 695213

Belzona products are
manufactured under an ISO
9000 Registered Quality
Management System.

www.belzona.com

