Belzona Protects Concrete Floor from Chemical Damage

ID: 5238

Industry: Chemical & Petrochemical Customer Location: South Carolina Application: FPA-Floor Problem Areas Application Date: July 2012

Substrate: Concrete

Products: * Belzona 5811 (Immersion Grade),

Problem

Floor, sumps and support pedestals are eroding due to sodium hypochlorate exposure to the concrete. Additionally, the sump drain has PVC which is a fire hazard and must be replaced. Chemicals will seep through the concrete into the ground if not contained.









Photograph Descriptions

- * Damage to concrete floor from chemical spill,
- * Seepage of sodium chlorate from previous product failure where the competitive product failed on adhesion ,
- st pH testing of concrete after power washed and prior to coating ,
- * Two coats of Belzona 5811 to drain and floor,

Application Situation

Concrete floor in a Chemical Process Building

Application Method

Power wash and remove any loose concrete, remove the previous epoxy from the sump containment well. Concrete was pH tested prior to application of material. Followed the IFU for Belzona 5811 as to cure and overcoat time. Belzona 5811 was applied in two coats with a roller and brush system.

Belzona Facts

Adhesion and protection from sodium hypochlorate was the princial reason Belzona 5811 was selected. The customer had a previous coating on the sump well floor and sides that delaminated and failed due to poor adhesion.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015
Belzona products are
FS 695214
manufactured under an ISO
ISO 14001:2015
9000 Registered Quality
EMS 695213
Management System.

BELZONA®
Repair • Protect • Improve