Belzona coating internal surface of sand filter tank

ID: 7707

Industry: Food & Drink

Application: TCC-Tanks and Chemical Containment

Areas

Substrate: Carbon Steel


Products: * Belzona 5311 (Ceramic immersion grade),

Problem

To protect the new fabricate sand filter tank from corrosion







Customer Location: Ayutthaya, Thailand

Application Date: 8 April 2016



Photograph Descriptions

- * 1. The new fabricate sand filter tank,
- * 2. Carbon steel surface was prepared by grit blasting,
- * 3. Apply first coat of Belzona 5311,
- * 4. Apply second coat of Belzona 5311,

Application Situation

Belzona coating the internal of new fabricate sand filter tank

Application Method

- 1. Carbon steel surface will be prepare by grit blasting with copper slag to give a minimum depth at 75 microns and surface cleanliness Sa 2.5
- 2. Clean and brush away any loose contaminate then cleaning the surface with Methyl Ethyl Ketone.
- 3. If found pitting damage area repair with epoxy putty.
- 4. Apply two coats system of Belzona 5311 Ceramic immersion grade at dry film thickness 400 microns.

Belzona Facts

Belzona 5311 (Ceramic Immersion Grade Black & Grey) is suitable for the intended purpose and will not result in adulteration of

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

www.belzona.com

BELZONA

food products, drinking water, potable water

www.belzona.com