# Belzona repairs a water slide in an amusement park

ID: 7985

Industry: General Industry Customer Location: France
Application: FPA-Floor Problem Areas Application Date: March 2019
Substrate: Composite - Glass fibre

Products: \* Belzona 2111 (D&A Hi-Build Elastomer),

\* Belzona 2121 (D&A Hi-Coat Elastomer),

#### Problem

The expansion joints were badly damaged by the rubber rings used on the slide. This was causing water infiltration in the little tunnel underneath the slide where customers can walk.









# **Photograph Descriptions**

- \* 1- Overview of the slide,
- \* 2- Previous joints removed,
- \* 3- Application of the elastomers,
- \* 4- Zoom on the finished repair,

# **Application Situation**

Expansion joints on a water slide

## **Application Method**

The previous expansion joints were removed, the substrate was manually abraded and the conditioner was applied. Then a foam rod was used at the bottom of the slot and Belzona 2121 was poured on top on the horizontal sections. Belzona 2111 was used for the vertical and curved sections. An applicator was then used to smoothen the surface of the elastomer and make sure that the joints were at the same level as the surface of the slide so the rubber rings would not damage it and the slot edges would not damage the rubber rings. This application has been carried out according to Belzona System Leaflet FPA-6.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA®
Repair • Protect • Improve

## **Belzona Facts**

Theses expansion joints had been repaired several times with a foam type material but the problem was persistent. The joints were either too big, and the rubber rings would tear them or they were too small and the rubber rings would get damaged by the edges of the slots. This customer already chose Belzona for other repairs on this slide and was happy with the result so he decided to use Belzona elastomers for this repair and was again, very happy with the result. Even if it seems like the joints only represent a small surface compared to the whole slide, around 45kg of elastomers were used for this project on around 90 meters of joints.