Belzona Seals Silo Flange

ID: 8141

Industry: Power Customer Location: Power Plant, Liverpool, UK

Application: GSS-Gaskets, Seals and Shims Application Date: November 2019

Substrate: Mild Steel

Products: * Belzona 2911 (Elastomer QD Conditioner),

* Belzona 2211 (MP Hi-Build Elastomer),

Problem

Mastic joint sealants are not bonded to the inside of the joint. As a result, when they shrink the sealant falls out, leaving a void for water and pollutant penetration into the dry powder.









Photograph Descriptions

- * 1. Silo showing the suspect flange joint,
- * 2. Leaking flange joint,
- * 3. Rope access contractor applying Belzona materials,
- * 4. Completed application on powder silo,

Application Situation

Dry powder silo had mastic sealant between flange joints which hardened and shrunk. This resulted in the mastic falling out leaving exposed gaps. The silo is tall and difficult to reach so using a specialist rope access contractor was the best option.

Application Method

The joint was cleaned out using a grinder making sure the joint upper and lower faces were rough. The flange face where the Belzona Elastomer was to be bonded was also manually prepared, cleaned and degreased prior to the application of Belzona 2911. Belzona 2211 was then applied to seal the flange face against moisture ingress. This application was completed in accordance with a modified version of Belzona System Leaflet GSS-11.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA

www.belzona.com

Belzona Facts Rope access was the only way to safely prepare the substrate with hand tools and apply the Belzona materials into the flange voids and over the flange face.