Belzona repairs & protects control valve

ID: 8889

Industry: Chemical & Petrochemical

Application: VPF-Valves, Pipes and Fittings

Substrate: Stainless-steel

Products: Belzona 1111 Supermetal

Belzona 1341 Supermetalglide

Belzona 2941 Conditioner

Belzona 2141 ACR Fluid Elastomer

Problem

Welding of this part would challenging due to the substrate involved. It would also not last in service any longer than the original metal.



Valve showing internal parts




Close up of the cavitation damage



Customer Location: Scotland

Application Date: November 2022

The damage rebuilt & the area coated with Belzona 1341 Supermetalglide



Belzona 2141 ACR Fluid Elastomer applied

Application Situation

A stainless steel control valve had suffered from cavitation erosion in service. The erosion had gone through wall in some areas of the valve body.

Application Method

The valve was disassembled, the critical parts were protected with blasting tape & then the internal surface was prepared to SA2.5 & 75 microns.

Belzona 1111 was then used to rebuild the lost metal. Two coats of Belzona 1341 Supermetalglide were then applied followed by one coat of Belzona 2141 ACR Fluid Elastomer.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

www.belzona.com



Belzona Facts By using the Belzona system the valve was able to be rebuilt easily with no risk of heat distortion. The combination of Belzona 1341 & Belzona 2141 provides excellent cavitation resistance for future protection from cavitation in service.

www.belzona.com