

Belzona Elastomer Restores an Expansion Joint in a Public Swimming Pool

ID: 9306

Industry: Local Authorities & Municipalities

Customer Location: France

Application: FPA-Floor Problem Areas


Application Date: July 2023

Substrate: Concrete

Products: Belzona 2211 (MP Hi-Build Elastomer), Belzona 2911 (Elastomer QD Conditioner)

Problem

At a municipal swimming pool, an expansion joint around one of the pool basins was found detached from its support. Chlorinated water had started to attack the concrete slab, causing leaks through the concrete and bringing dampness to the equipment room in the basement. In addition, there was a greasy deposit from the old silicone expansion joints. This resulted in slipperiness which posed a serious risk of pool users falling over.



Measurement of the defective expansion joint in order to calculate the required quantity of product.



The application area was marked with tape to delimit the application area. A backer rod was inserted into the joint prior to the application of Belzona 2211.



Belzona 2211 filled the expansion joint, safeguarding the concrete structure underneath from further damage.

Application Situation

The application took place while the pool was closed, allowing the area to be kept free of water. A water inlet box near the the application area was removed to allow the access to the expansion joint. Belzona 2211 was identified to be the most suitable solution in this case.

Application Method

The application was carried out in accordance with Belzona Know-How System Leaflet FPA-6.

The old silicone expansion joint was removed and a grinder was used to prepare the surface for the application of Belzona. The area of defective joint was measured to calculate the product required to complete the application. Masking tape was utilised to properly mark and delineate the application area and to maintain a clean finish.

A thin layer of Belzona 2911 (Elastomer QD Conditioner) was applied to the prepared surface and allowed to dry before a backer rod was inserted into the joint. Humidity level was also checked using a hygrometer to ensure suitable atmospheric conditions for the application.

Belzona 2211 (MP Hi-Build Elastomer) was then thoroughly mixed and applied to the joint to form a new expansion joint.

Belzona Facts

Belzona 2211 was chosen as the solution to this problem in the swimming pool thanks to its resistance to chlorinated water.

For more examples of Belzona Know - How In Action, please visit <https://khia.belzona.com>

ISO 9001:2015

Belzona products are

FS 695214

manufactured under an ISO

ISO 14001:2015

9000 Registered Quality

EMS 695213

Management System.

www.belzona.com



Furthermore, the solution provided perfect waterproofing and able to adapt to the movement of the substrates. The application was completed within 1.5 days, resulting in a fast and labour-efficient solution.

For more examples of Belzona Know - How In Action, please visit <https://khia.belzona.com>

ISO 9001:2015
FS 695214
ISO 14001:2015
EMS 695213

Belzona products are
manufactured under an ISO
9000 Registered Quality
Management System.

www.belzona.com

