

## **Belzona 1111 Can Rebuild Severe Pump Corrosion**

ID: 9451

Industry: Not Specified Customer Location: Washington Application: PDP-Positive Displacement Pumps Application Date: September 2015

Substrate: Cast Iron

Products: Belzona 1111 (Super Metal)

**Problem** 

Heavy metal loss on the internal components of a multi-stage vertical salt water pump.









Original condition after opening the pump.

Up close view of the damage.

damage and correcting the profile.

Belzona 1111 filling in all of the A look at the other side of the piece after the Belzona 1111 application.

## **Application Situation**

Deep pitting on the internal parts were causing poor performance with this pump.

## Application Method

Grit blasting to prepare the surface according to the Belzona 1111 Instructions For Use. Then the Belzona 1111 was applied by hand using the Belzona applicator. Once cured, the application was hand sanded to the original profile and coated with two full coats of Belzona 1341N.

## **Belzona Facts**

Replacement was not an option as this was an older pump. Replacement would involve a new model pump which would require additional work to get it to match up to the existing system. This repair was done in two days, and the pump was ready to be reassembled and put back into service. Inspection of the pump during routine maintenance three years later showed no further damage, and the pump has continued to run more efficiently than it had for several years prior.