

BELZONA PROTECTS CONDENSOR JOINT FOR TWENTY YEARS

ID: 1184

Industry: Power
Application: VPF-Valves, Pipes and Fittings
Substrate: Carbon Steel
Products: <div>Belzona® 1311 (Ceramic R Metal)</div><div>Belzona® 1321 (Ceramic S Metal)</div>

Customer Location: Nuclear Plant, USA
Application Date: 1989

Problem

Joints could not be replaced in the short nuclear plant refueling outage. Corrosion had caused holes in the metal expansion joints.



Photograph Descriptions

* The original repair , * Overall view of the repair , * Rebuild with Belzona® 1311 , * Two coats of Belzona® 1321 applied over the joints ,

Application Situation

Carbon Steel expansion joints below the condenser corroding due to bimetallic corrosion.

Application Method

Application carried out in accordance with Belzona Know-How System Leaflets VPF-1 & -2.

Belzona Facts

First repair lasted 20 years. Although the unit had been down 10 of those years. When the unit was restarted the engineers inspected the old Belzona and found it in excellent shape with only minor damage. It was decided to remove the old Belzona and rework the project. A dozen joints were repaired and coated.

For more examples of Belzona Know - How In Action, please visit <https://khia.belzona.com>

ISO 9001:2015
FS 695214
ISO 14001:2015
EMS 695213

Belzona products are
manufactured under an ISO
9000 Registered Quality
Management System.

www.belzona.com

BELZONA
Repair • Protect • Improve