

Belzona Strengthens Laydown Deck

ID: 3204

Industry: Oil & Gas Customer Location: UK North Sea

Application: GSS-Gaskets, Seals and Shims Application Date: 2004

Substrate: Carbon Steel

Products: * Belzona® 1111 (Super Metal),

* Belzona® 5811 (Immersion Grade),

Problem

The deck had become weakened through daily operation (lowering/removal of containers) and weather. The original 8mm steel deck was corroded through wall in many locations. welding was not an option due to the installed underr-deck passive fire protection.









Photograph Descriptions

- * Condition of deck prior to starting work,
- * Installation of deck reinforcement,
- * Completed works,
- * Inspection in 2015,

Application Situation

Offshore Oil Platform Laydown Deck

Application Method

A modified version of Belzona System Leaflet GSS-9 was employed. 5mm steel plates, drilled to accept jacking bolts and injection ports, were prepared by gritblasting and positioned onto the gritblasted deck. The jacking bolts were used to obtain accurate levels. The circumference of the plates were sealed using Belzona® 1111. Belzona® 5811 was injected into the void using an airless pump to seal and bond the reinforcement plate to the deck with 100% contact area being achieved.

Belzona Facts

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

www.belzona.com



Independent testing showed that the Belzona bonding method in this case was equivalent in strength to a welded plate, stiffer AND more elastic than the original 8mm plate, good resistance to impact loading, and considered by the independent engineering designers to be "robust enough to withstand the rigours of laydown area operations. The key benefits were that daily operations were not interrupted and that the passive fire protection in the machinery space below would not be affected. This work has been inspected annually and has resulted in other deck strengthening projects being undertaken. Last feedback and inspection image received in 2015, engineers are still delighted with the work.