# BELZONA REPAIRS EBONITE LINING IN PROCESS VESSEL

ID: 3414

Industry: Chemical & Petrochemical Customer Location: International chemical company, Spain

Application: TCC-Tanks and Chemical Containment Application Date: April 2012

Areas

Substrate: Ebonite and steel

Products: \* Belzona® 4301 (Magma CR1 Hi-Build),

### **Problem**

The internal ebonite lining was damaged around the vessel support areas where the ebonite had disbonded leaving the steel exposed.









### **Photograph Descriptions**

- \* Ebonite lining damaged around support areas,
- \* Surface preparation completed,
- \* Belzona® 4301 being applied on the internal supports areas,
- \* Completed application ,

### **Application Situation**

Ebonite lined process vessel operating with 10-35% Hydrochloric acid.

## **Application Method**

The application was carried out in accordance with Belzona Know-How System Leaflet TCC-3. The surface was prepared removing the previous mastic products. Then, the ebonite was roughened using a grinder and the whole application area was grit blasted to ensure a minimum 75 micron surface profile on the exposed steel before rebuilding all damaged areas with the Belzona® 4301.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA

www.belzona.com

# Belzona Facts This application was carried out in-situ, repairing the ebonite lining without the requirement of a vulcanization process, and minimising downtime and disruptions to the client facilities and operations.