RUDDER PINTLE REBUILT WITH BELZONA 1111

ID: 6004

Industry: Marine

Application: MPT-Mechanical Power Transmission

Substrate: Steel

Products: * Belzona 1111 (Super Metal),

Problem

Shaft was corroded and pitted from salt water.







Customer Location: Portland, OR, USA

Application Date: November 2015



Photograph Descriptions

- * Shaft already machined down, some damage still visible. ,
- * Rough cut thread pattern.,
- * Applying Belzona 1111.,
- * Completed application, finishing with emery cloth.,

Application Situation

Rudder pintle shaft on a 700' US Navy ship.

Application Method

All of the damaged areas were removed with a lathe. The surface was then prepared with the lathe to leave a super rough thread pattern to ensure a full mechanical bond. Again, using the lathe, Belzona 1111 was applied with a slow rotation. After a sufficient amount of material was applied, Belzona 1111 was allowed to fully cure and then machined to the required specifications. There was one low spot and a couple of air pockets visible, so those areas were once again abraded and a further layer of Belzona 1111 was applied and allowed to cure before the final machine cut was made. The final finish was made using emery cloth, leaving a perfect smooth finish.

Belzona Facts

Welding would risk warping the shaft and would have taken probably close to ten times the man-hours to complete. The actual

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA®

www.helzona.com

ime spent on this process was no more than 6 hours, not including cure time.	
for more examples of Belzona Know - How In Action, please visit https://khia.belzona.com	