Saving the belt with Belzona!

ID: 7497

Industry: Food & Drink Customer Location: WA, USA

Application: SHM-Solids Handling Machinery Application Date: June 2017

Substrate: Rubber and Fiber

Products: * Belzona 2911 QD Conditioner Belzona 2111 D&A Hi-Build Elastomer Belzona 9341 Reinforcing Sheet,

Problem

Corn and soybeans falling as the conveyor belt lifts the grains up was causing enough abrasion on the backside of this vertical belt to wear off a complete layer of rubber leaving the layer of the fiber exposed. The wear is worse right next to the joint actually wearing through the fiber layer.









Photograph Descriptions

* 1. The silos. 2. Belt prep and Belzona 2911 QD Conditioner. 3. First layer of Belzona 2111 D&A Hi-Build Elastomer. 4. Application complete.,

Application Situation

2 - 50" Conveyor belts lifting grain from rail cars to silos.

Application Method

Pressure washed the application area to remove debris and grain dust. Used a handheld wire brush to roughen the fiber surface as the majority of the rubber layer was loose and disbonded and was removed. The outline of the proposed application area was marked and the Belzona 2911 QD Conditioner was applied and allowed to dry per the IFU. Duct tape was applied over the joint seam to allow the application to bridge rather than adhere. The outline was also taped off just inside of where the conditioner was applied. Only one unit of Belzona 2111 D&A Hi-Build Elastomer was mixed at a time, the first batch used to wet out the application area, the second added some volume as well as wetting out the Belzona 9341 Reinforcing Sheet. The last batch smoothed out the application and covered the reinforcing sheet completely.

Belzona Facts

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

www.belzona.com

BELZONA

Only 3 units of Belzona 2111 D&A Hi-Build Elastomer were used on this project. The alternative is to replace the belts which reach over 10 stories straight up and would cause extended downtime. This repair took 4 hours and will protect the belt from the highly abrasive grain.

