# Belzona repair and coating internal surface of wil tray machine

ID: 7711

Industry: Food & Drink

Application: CEP-Centrifugal Pumps

Substrate: Carbon Steel

Products: \* Belzona 1121 (Super XL-Metal),

\* Belzona 5892,

### **Problem**

Corrosion at internal surface of wil tray machine.







Customer Location: Bangkok, Thailand

Application Date: 23 December 2016



### **Photograph Descriptions**

- \* 1. Corrosion found at internal surface of wil tray machine. ,
- \* 2. Apply first layer with Belzona 5892,
- \* 3. Repaired pitting damage area with Belzona 1121,
- \* 4. Apply second layer with Belzona 5892,

### **Application Situation**

Repair and coating internal surface of wil tray machine wide 1.6 m. length 16 m.

## **Application Method**

- 1. Carbon steel surface will be prepare by grit blasting with copper slag to give a minimum depth at 75 microns and surface cleanliness by Swedish standard Sa 2.5
- 2. Clean and brush away any loose contaminate then cleaning the surface with MEK.
- 3. Apply first coat with Belzona 5892 HT Immersion grade at dry film thickness 200 microns.
- 4. If find pitting damage area repair with Belzona 1121 Super XL Metal.
- 5. Apply second coat with of Belzona 5892 HT Immersion grade at dry film thickness 200 microns.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA®

www.belzona.com

# Belzona Facts Belzona 5892 exhibits low surface bloom and excellent inter-coat adhesion enabling 2-coat application without the need for frost blasting. It has been formulated in light colours to assist visibility and provide good inspection characteristics in poorly lit vessels.