FAST REPAIR OF BUTTERFLY VALVES WITH BELZONA ELASTOMERS RETURNS VESSEL TO SERVICE ON TIME

ID: 7754

Industry:MarineCustomer Location: Oregon, USAApplication:VPF-Valves, Pipes and FittingsApplication Date: September 3, 2018

Products: * Belzona 2121 (D&A Hi-Coat Elastomer),

Steel and existing rubber boot

* Belzona 2911 (Elastomer QD Conditioner),

Problem

Substrate:

Two valves were damaged as the rubber boot that provided the sealing surface had suffered damage. One appeared to be damaged by debris that was in the way while the valve was closed removing a large piece of rubber material. The other valve was damaged at the seating area probably during installation.









Photograph Descriptions

- * 1. The Customer was excited to use Belzona to complete the repair. ,
- * 2. Valve 1 with a large piece of rubber boot missing after surface preparation. ,
- * 3. Valve 2 with damage on the seating area after surface preparation. ,
- * 4. Repaired valves.,

Application Situation

Two butterfly valves that control the flow of seawater in a vessel. The valves needed to be repaired to return the vessel to water on time.

Application Method

A modified version of Belzona System Leaflet VPF-3 was used to repair the valve lining. Loose material was removed and rubber

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA®
Repair • Protect • Improve

substrate was undercut to avoid a feathered edge. Application area was thoroughly degreased to remove contamination. Steel substrate was ground and rubber substrate was abraded with roughening brush to create a surface profile for Belzona 2121 (an ABS approived product) to achieve a mechanical bond. The surface was then conditioned with a light coat of Belzona 2911 and allowed to cure. The areas of concern were then masked off and then Belzona 2121 was poured into place. The masking tape was removed immediately and the product was left to cure. After the product had cured the repair areas were machined back to tolerance.

Belzona Facts

New boots were ordered for the valves but upon receiving them the boots did not fit. Due to a holiday weekened the Customer chose a Belzona solution as the product and technical assistance were available on short notice. After the product was cured the valves were hydro tested to ensure the valves would hold pressure and they passed the test.