# Belzona repairs a raw mill in a cement industry

ID: 7986

Industry:Mining & QuarryingCustomer Location: IrelandApplication:SHM-Solids Handling MachineryApplication Date: 2014

Substrate: Mild Steel

Products: \* Belzona 1111 (Super Metal),

#### Problem

There are three rollers per mill and there are 12 wear plates (1200kg each) per roller. The clamps are fixed with 4 large bolts. There was play between the wear plate and the roller and the bolts and clamps were failing, leading to a forced stoppage of the mill.









## **Photograph Descriptions**

- \* 1- Before application,
- \* 2- After surface preparation,
- \* 3- After application of Belzona 1111,
- \* 4- Final application,

### **Application Situation**

Wear plates on rollers

#### **Application Method**

The application was done in accordance with Belzona System Leaflet SHM-8. Two wear plates were removed from the roller at a time and the area on the roller was grit blasted. The back of the new wear plate was also grit blasted and Belzona 1111 was applied to the roller in a layer of approximately 2cm thick in the position corresponding to one wear plate. The wear plate was then fitted onto the wet Belzona 1111 to create a perfect seat. The process was repeated until 12 wear plates had been installed.

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA®
Repair • Protect • Improve

#### **Belzona Facts**

Belzona 1111 was chosen by the customer here because it has the required properties for this specific application (high compressive strength, workability, etc) This application has been 100% successful since 2014. This job is repeated annually when the wear plates are being replaced. The quantity of material for 1 roller is 12 x 2kg or 36 x 2kg of Belzona 1111 per mill. There are 2 mills in this factory (raw mill and cement mill) which are very similar.

www.belzona.com