Abrasion Protection of Linatex Tower

ID: 8162

Industry: General Industry Customer Location: Quarry, Scotland UK

Application: SHM-Solids Handling Machinery Application Date: 2019

Substrate: Steel

Products: * Belzona 1321 (Ceramic S-Metal),

* Belzona 1812 (Ceramic Carbide FP),

* Belzona 9811,

Problem

The abrasive qualities of sand had resulted in wear and holes on the steel chute. The equipment only lasted six months before wearing out, so a more permanent solution was required by the client.









Photograph Descriptions

- * Equipment prior to coating ,
- * Application of Belzona 1321,
- * Tiles grouted in-place ,
- * Completed application after six months in service ,

Application Situation

Sand drops into the entrance of the chute causing excessive wear.

Application Method

Belzona 1321 was used as an adhesive for the Belzona 9811 Alumuina tiles. They were then grouted in with Belzona 1812. As not to

For more examples of Belzona Know - How In Action, please visit https://khia.belzona.com

ISO 9001:2015 Belzona products are
FS 695214 manufactured under an ISO
ISO 14001:2015 9000 Registered Quality
EMS 695213 Management System.

BELZONA®

waste the left of material, Belzona 1812 was then applied over the tiles. The application was carried out in accordance with Belzona System Leaflet SHM-7.

Belzona Facts

The service life of this part in normally six months. Fabrication of a new chute cost around £500, plus a day lost for production every 6 months. The cost of the Belzona repair was 25% less and is still showing no signs of deterioration.

www.belzona.com