BELZONA EMERGENCY RECLAMATION OF A REFINER

ID: 953

Industry: Pulp & Paper Customer Location: Paper mill, United Kingdom

Application: PDP-Positive Displacement Pumps Application Date: August 2000.

Substrate: Cast Iron

Products: Belzona® 1311 (Ceramic R Metal)<div>Belzona® 1321 (Ceramic S Metal)

</div>

Problem

Severe erosion in the refiner body and the end cover/door led to several holes necessitating repair









Photograph Descriptions

* Refiner case prior to the application in 2000, * The August 2000 rebuild and coating, * After seven years and one intermediate coating, still in excellent condition. The repair area was between the top two bolt holes, * Close-up after application of another coat of Belzona® 1321,

Application Situation

Disc refiner

Application Method

The original application was carried out in accordance with Belzona Know-How System Leaflet PDP-6.

Belzona Facts

In 2004 the refiner was inspected and a further coat of Belzona® 1321 was applied. Now in December 2007 it has been checked again and found still to be in excellent condition.